

Registrar of Regulations	Date/Time Filed with Registrar of Regulations
AUTHORIZATION TO FILE DOCUMENTS INCORPORATED BY REFERENCE BY DESCRIPTION	8-4-15 9:54a.m.

1 Agency: State Water Control Board

2 Regulation Numbers: VR VAC 9VAC25-91
 Title of Regulation: Facility and Aboveground Storage Tank (AST) Regulation

3 Effective Date of Regulation: Nov 1, 2015


4 Name of Document Incorporated by Reference:
 National Association of Corrosion Engineers (NACE) SP0285-2011, "Corrosion Control of Underground Storage Tank Systems by Cathodic Protection"

5 Attach a summary of the document incorporated by reference, including publication date and a copy of the cover page.

<p>6 Document available for inspection at the following location: <u>Department of Environmental Quality, Petroleum</u> <u>Program, 629 East Main Street, Richmond, VA 23219</u> <u>(mailing: P.O. Box 1105, Richmond, VA 2318)</u></p>	<p>7 Copy of referenced document may be procured from: <u>NACE International, 1440 South Creek Drive,</u> <u>Houston, TX USA 77084-4906, Phone: 281-228-6200</u> <u>www.nace.org</u></p>
--	---

8 Exemptions Claimed Under (Specific Reference):
 Administrative Process Act _____
 Virginia Register Act _____
 Virginia Code Commission Regulations Section 3.3 B 5

Request submitted by: Cindy M. Berndt
Name
Director, Office of Regulatory Affairs, DEQ 7/29/2013
Title Date

Approved:  8/5/15
Registrar of Regulations Date



NACE SP0285-2011
(formerly RP0285)
Item No. 21030

Standard Practice

External Corrosion Control of Underground Storage Tank Systems by Cathodic Protection

This NACE International standard represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone, whether he or she has adopted the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not in conformance with this standard. Nothing contained in this NACE International standard is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by Letters Patent, or as indemnifying or protecting anyone against liability for infringement of Letters Patent. This standard represents minimum requirements and should in no way be interpreted as a restriction on the use of better procedures or materials. Neither is this standard intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this standard in specific instances. NACE International assumes no responsibility for the interpretation or use of this standard by other parties and accepts responsibility for only those official NACE International interpretations issued by NACE International in accordance with its governing procedures and policies which preclude the issuance of interpretations by individual volunteers.

Users of this NACE International standard are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and for determining their applicability in relation to this standard prior to its use. This NACE International standard may not necessarily address all potential health and safety problems or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this standard. Users of this NACE International standard are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities if necessary, to achieve compliance with any existing applicable regulatory requirements prior to the use of this standard.

CAUTIONARY NOTICE: NACE International standards are subject to periodic review, and may be revised or withdrawn at any time in accordance with NACE technical committee procedures. NACE International requires that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of initial publication. The user is cautioned to obtain the latest edition. Purchasers of NACE International standards may receive current information on all standards and other NACE International publications by contacting the NACE International *FirstService* Department, 1440 South Creek Drive, Houston, Texas 77084-4906 (telephone +1 281-228-6200).

Revised 2011-03-13
Revised 2002-04-06
Revised February 1995
Approved March 1985
NACE International
1440 South Creek Dr.
Houston, Texas 77084-4906
+1 281-228-6200
ISBN 1-57590-143-9

© 2011, NACE International

Foreword

This standard presents standard practices for effective control of external corrosion of underground storage tank (UST) systems by cathodic protection (CP). It is intended to be used by corrosion professionals as a guideline to establish minimum requirements for using CP to control external corrosion of metallic UST systems, including those used to contain oil, gas, and water. Specifically addressed is CP of:

- (a) Existing bare and externally coated steel USTs;
- (b) New externally coated steel USTs;
- (c) Metallic piping and flexible connectors; and
- (d) Other metallic components.

For further information on testing CP systems for UST systems, refer to NACE Standard TM0101.¹

This standard was originally published in 1985 by Task Group (TG) T-10A-14, "Control of External Corrosion on Metallic Buried, Partially Buried, or Submerged Liquid Storage Systems." The standard was revised in 1995 by TG T-10A-14, "Corrosion Control of Underground Storage Tank Systems," a component of Unit Committee T-10A, "Cathodic Protection." It was revised in 2002 and in 2011 by TG 011, "Corrosion Control of Underground Storage Tank Systems by Cathodic Protection." TG 011 is administered by Specific Technology Group (STG) 35, "Pipelines, Tanks, and Well Casings," and is sponsored by STG 05, "Cathodic/Anodic Protection." This standard is issued by NACE International under the auspices of STG 35.

In NACE standards, the terms *shall*, *must*, *should*, and *may* are used in accordance with the definitions of these terms in the *NACE Publications Style Manual*. The terms *shall* and *must* are used to state a requirement, and are considered mandatory. The term *should* is used to state something good and is recommended, but is not considered mandatory. The term *may* is used to state something considered optional.

**NACE International
Standard Practice**

**External Corrosion Control of Underground Storage Tank Systems
by Cathodic Protection**

Contents

1. General	1
2. Definitions	1
3. Cathodic Protection of New Underground Storage Tank Systems.....	3
4. Cathodic Protection of Existing Underground Storage Tank Systems	6
5. Criteria for Cathodic Protection	9
6. Cathodic Protection System Design	10
7. Installation of Cathodic Protection Systems	14
8. Operation and Maintenance.....	18
References	20
TABLES	
Table 1: Conversion of Other Potential Measurements to CSE Equivalents.....	10

Section 1: General

1.1 Introduction

1.1.1 This standard presents standard practices for effective control of external corrosion of UST systems by CP. It is intended to serve as a guideline to establish minimum requirements for using CP to control external corrosion of metallic UST systems, including those used to contain oil, gas, and water, and that are buried, partially buried, or in contact with the soil.

1.1.2 When designing the CP system, the designer shall provide the owner with the design life and the assumptions used to develop the CP system design. If conditions change at the UST site, the original CP system design life may also change. Some examples of UST system changes include fluctuation in soil resistivity, UST system coating failure, adding/removing components of the UST system or site, and electrical shorting or isolation of UST components. This information should be kept as part of the permanent UST system records.

1.1.3 This standard does not designate specific practices for every situation because the complexity of some environmental conditions in which UST systems are buried precludes standardization of corrosion control practices.

1.1.4 This standard does not include corrosion control methods based on chemical control of the environment, internal linings, or the use of UST construction materials other than steel.

1.1.5 This standard does not override applicable safety codes and should not be used to infringe on the primary requirement of protecting personnel, the environment, and equipment. In any situation, the CP system design for UST systems should incorporate all requirements of any applicable codes, standards, and regulations as determined by authorities having jurisdiction.

1.1.6 The provisions of this standard shall be applied under the responsible direction of competent individuals. Such individuals must either be registered professional engineers, NACE International certified Corrosion Specialists or CP Specialists, or individuals qualified by professional education and related practical experience. All of the above individuals must be able to demonstrate suitable experience in corrosion control of UST systems.

1.1.7 Deviation from this standard may be warranted in specific situations provided the objectives expressed in this standard have been achieved.

1.1.8 For accurate and correct application of this standard, this standard must be used in its entirety. Using or referring to only specific paragraphs or sections can lead to misinterpretation and misapplication of the standard practices contained in the standard.

Section 2: Definitions

Anode: The electrode of an electrochemical cell at which oxidation occurs. (Electrons flow away from the anode in the external circuit. It is usually the electrode where corrosion occurs and metal ions enter solution.)

Backfill: Material placed in a hole to fill the space around the anodes, vent pipe, and buried components of a cathodic protection system.

Cathode: The electrode of an electrochemical cell at which reduction is the principal reaction. (Electrons flow toward the cathode in the external circuit.)

Cathodic Disbondment: The destruction of adhesion between a coating and the coated surface caused by products of a cathodic reaction.

Cathodic Polarization: (1) The change of electrode potential caused by a cathodic current flowing across the electrode/electrolyte interface; (2) a forced active (negative) shift in electrode potential. (See *Polarization*.)

Cathodic Protection: A technique to reduce the corrosion rate of a metal surface by making that surface the cathode of an electrochemical cell.